

**ELEVATED TEMPERATURE OXIDATION PROTECTION COATINGS FOR
TITANIUM ALLOYS AND METHODS OF PREPARING THE SAME**

ABSTRACT OF DISCLOSURE

5

Oxidation protection of a titanium-based alloy is provided with improved fatigue properties by a titanium aluminide coating of between 2 to 12 microns by diffusing the Al into the Ti at a temperature below the melting point of the Al. The coating is gas deposited and protects the titanium-based alloys from oxidation at

10

high temperature utilization.